AD

AD551062

Report 1893

THE KINETICS OF THE THERMAL DECOMPOSITION

OF MOLTEN SILVER AZIDE

by

Dr. Herbert J. Mueller

March 1967

U. S. ARMY ENGINEER RESEARCH AND DEVELOPMENT LABORATORIES
FORT BELVOIR, VIRGINIA

U. S. ARMY ENGINEER RESEARCH AND DEVELOPMENT LABORATORIES
FORT BELVOIR, VIRGINIA

Report 1893

THE KINETICS OF THE THERMAL DECOMPOSITION

OF MOLTEN SILVER AZIDE

Task 1C014501A32B

March 1967

Distributed by

The Commanding Officer
U. S. Army Engineer Research and Development Laboratories

Prepared by

Dr. Herbert J. Mueller
Basic Research Laboratory
Military Technology Department

SUMMARY

This report covers an investigation of the thermolysis of molten silver azide (AgN_3), which process is considered to be fundamental for the ignition of the explosive by thermal stimulus.

The isothermal decomposition of molten silver azide was investigated in the temperature interval 309-340° C. Decomposition was found to occur at the metal-azide interface with an activation energy of 38 ± 2.5 kcal/mole. Initially, the decomposition proceeds at a constant rate. After a while the reaction becomes accelerated as a result of the formation of silver nuclei in the melt. The rate of reaction is then proportional to the third power of time, and an apparent activation energy of 138 ± 5 kcal/mole is measured. The activation energy for the growth of silver nuclei in the melt is estimated to be ca. 24 kcal/mole. The latter value can be interpreted as the activation energy for the migration of interstitial silver in the azide matrix.

FOREWORD

Authority for the research covered by this report is contained in Task 1C014501A32B.

The study was made by Dr. H. J. Mueller, Assistant Director, Basic Research Laboratory, assisted by Messrs. R. J. Holland and C. S. Fox.

Acknowledgment is made to Dr. Z. V. Harvalik, Director, Basic Research Laboratory, for his encouragement in this endeavor.

CONTENTS

THE KINETICS OF THE THERMAL DECOMPOSITION

OF MOLTEN SILVER AZIDE

I. INTRODUCTION

When silver azide is brought to temperatures above 340° C, it detonates after a certain delay time. This "induction period" is a function of temperature. On heating the silver azide above 390° C, the ignition delay is very short, and the impression of a spontaneous detonation results. At lower temperatures the induction period may amount to several minutes. Microscopic observation and high-speed motion pictures show that during the induction period the azide melt bubbles vigorously, while floats of metallic silver are formed on the surface of the melt droplet. The evolution of substantial amounts of nitrogen is observed and indicates that thermolysis occurs during the initial phase of the initiation process.

The thermal decomposition of silver azide has been studied quantitatively for the solid phase only. Audubert (ref 1) calculated activation energies of 38-40 kcal/mole from nitrogen evolution measurements, as compared to 46 kcal/mole from chemiluminescence experiments. By use of the former method, Bartlett, Tompkins, and Young (ref 2) obtained 44-46 kcal/mole for the decomposition of the low-temperature form, and 31-32 kcal/mole for the high-temperature modification of silver azide. They were able to interpret the mechanism of the solid state decomposition of this salt in terms of the electron band model of the azide crystal. Silver azide, however, detonates from the melt (ref 3), and kinetic data obtained from the solid state work are consequently of limited value for an understanding of the mechanism of thermal initiation of this salt. Hence, it was the purpose of the author to study the thermolysis of molten silver azide, which process is fundamental for the ignition of the explosive by thermal stimulus.

II. INVESTIGATION

The silver azide used in this investigation was prepared by standard techniques from highly pure silver nitrate and sodium azide and was further purified by crystallization. Colorless, prismatic crystals of silver

azide (1-5 mm) were grown from aqueous solution.[1] When these crystals were handled gently, they could be cleaved without detonating. If the crystals were allowed to age, even though they were shielded from light, they developed a faint pinkish coloration which, it is believed, was caused by the formation of silver nuclei of colloidal dispersion.[2] After the silver azide was heated, it underwent a phase transition in the solid state at 190° C.[3] The originally colorless and transparent crystals suddenly became yellow and opaque. When the crystals were recooled below the transition point, they became discolored immediately. The opaque appearance, however, remained. The opacity was probably caused by cracking of the crystals along small angle boundaries during the transition from the low- to the high-temperature modification. Molten silver azide (m.p. = 309° C)[4] is a yellow liquid of honey-like consistency, which bubbles continuously because of thermal decomposition. When the melt is brought to a temperature above 340° C, the yellow color of the droplet changes to a dark purple and detonation occurs.

Silver azide decomposes according to

$$AgN_3 \rightarrow Ag + N_2 . \qquad (1)$$

No secondary reactions are known, and the course of the reaction can be followed by measuring the nitrogen evolution as a function of temperature

---

1. The author is indebted to J. L. Taylor and R. L. Brooks, Basic Research Laboratory, for supplying silver azide crystals.

2. A similar coloration, which is well-known for aged or slightly reduced silver halides (photohalides), has been proved to have resulted from the presence of colloidal metal.

3. The low-temperature modification is orthorombic, according to Pfeiffer (ref 4). The structure of the high-temperature modification is still unknown. Preliminary x-ray measurements by J. Joebstl (private communication) indicate a rhombohedral structure.

4. Considerably lower melting points for silver azide are given occasionally in the literature. Measurements performed in the Basic Research Laboratory showed that freshly prepared pure AgN_3 melts at 309° C (private communication with J. Joebstl). Lower melting points are associated with impure or partially decomposed material.

and time.   This method was used in the Basic Research Laboratory exper-
iments, and the apparatus employed is shown in Fig. 1.   The bottom of the
reaction vessel (V) was kept at the chosen temperature by means of a ther-
mostatically controlled metal bath (H).   The nitrogen evolution was meas-
ured by a cold-cathode ionization pressure gauge (G).   The output of the
gauge was registered continuously by a strip chart recorder.


Fig. 1.   Decomposition apparatus: Reaction tube (V);   thermostatic-
ally controlled metal bath (H);   liquid nitrogen trap (D);   pressure
gauge (G);   magnetic sample drop device (S);   and thermocouple (TC).

At the beginning of the experiment, a crystal of ca. 0.5-mg weight was placed into the sample pan of the magnetic drop device (Fig. 2). The entire system was carefully evacuated and kept at 10^{-5} torr for 1 hour. After this time, the reaction vessel was isolated from the diffusion pump, and the system was cryogenically pumped with liquid nitrogen for an additional 30 minutes. The measurement was started by dropping the sample crystal into the bottom of the hot reaction tube. A new pyrex tube was used for each run. The gas pressure in the system is influenced by the length of tubing that is immersed in the liquid nitrogen of the cooling trap; therefore, a special dewar (D in Fig. 1) was designed, so that the length of the cooled tubing was independent of the level of the coolant in the trap.


Fig. 2. Enlargement of magnetic sample drop device (S). When the steel hook (H) is released by the approaching magnet (M) to the wall of the reaction tube (V), the platinum sample pan (P) tilts downward and the specimen drops into the bottom of V.

The reproducibility of the first measurements was discouragingly poor, although utmost care was taken to use good crystals of equal weight and shape. Microscopic observation of melting crystals of silver azide indicated that the lack of reproducibility was a result of the unpredictable pattern in which the viscous, nonwetting melt spread out on a glass surface. In order to correct this situation, the bottom of the reaction tube was filled with glass beads of approximately 30-micron diameter. The spaces between the beads acted as a system of fine capillaries, into which the melt

4

seeped nearly instantaneously. The capillary forces caused the liquid azide to spread evenly on the glass interface. By use of this method, well-reproducible results were obtained immediately. No evidence of self-heating of the decomposing sample was found under the experimental conditions of this study.

Typical decomposition curves are shown in Fig. 3. A remarkable feature is the occurrence of two distinct patterns of reaction. When the sample is dropped, the nitrogen pressure in the system starts to build up


Fig. 3. Decomposition curves of silver azide.
(Note the larger time scale of curve A.)

at a constant rate, and the pressure vs time diagram is a straight line. After a while, the reaction usually changes its pace and becomes accelerated. The onset of the acceleration occurs earlier at higher temperatures. The linear branch may shrink to a minor irregularity of the decomposition curve at the beginning of the experiment. On the other hand, the linear reaction persists without any acceleration when the sample temperature is not too far above the melting point.

The linear branch of the decomposition is typical for a first-order reaction, which takes place at an interface of constant area. From the Arrhenius plot, an activation energy of $\epsilon_I = 38 \pm 2.5$ kcal/mole was obtained for this phase of the reaction (Fig. 4). Microscopic observation of the decomposing sample showed that immediately after melting of the specimen, the glass-azide interface is covered with thin silver flakes, and floats of metallic silver appear on the free surface of the melt. Gas


Fig. 4. Arrhenius plot for the thermolysis of silver azide (time-linear reaction, k in arbitrary units).

bubbles were observed to rise from silver particles only; thus, it must be concluded that decomposition occurs predominantly at the silver-silver azide interface.

III. DISCUSSION

If the onset of the accelerated reaction is taken as zero time, and if the total pressure background produced by the linear reaction is properly subtracted, the pressure buildup (P) during the accelerated phase of the reaction can be plotted as a power of time, with an exponent of four

$$P_{accel.} \sim t^4 \qquad (2)$$

The exponents in individual runs have been found to vary between 4.2 and 3.7; the lower values are predominantly observed at higher temperatures. It was impossible to calculate the activation energy for the accelerated reaction with some accuracy from "mixed" curves (C in Fig. 3) because of the difficulty of determining exactly the new zero point of the time axis. Experience showed, however, that freshly prepared crystals occasionally gave decomposition curves of type B also at relatively low temperatures. Hence, a number of crystals of equal weight from one particular batch were selected and were decomposed either at 326^0, 329^0, or 332^0 C. Only those curves which showed the t^4-law from the beginning were considered for evaluation. The specific rates obtained from these runs were averaged and used for an Arrhenius plot from which an apparent activation energy of $\epsilon_{II} = 138 \pm 5$ kcal/mole was finally computed.

Power laws (e.g. as represented in equation (2)), with exponents between 2 and 8 frequently have been found to govern the thermolysis of metal azides (ref 5). These laws have been interpreted in terms of formation and growth of metal nuclei and resultant acceleration of the thermolytical reaction. The occurrence of a t^4-law, in particular, is indicative of a first-order reaction which takes place on the surface of three-dimensional, steadily growing metal nuclei, while new nuclei are being formed constantly. According to the theory, the apparent activation energy ϵ_{II} then consists of three times the activation energy for one-dimensional nucleus growth ϵ_G, plus the activation energy for the formation of new nuclei ϵ_F

$$\epsilon_{II} = 3\epsilon_G + \epsilon_F . \qquad (3)$$

7

Generally, it is complicated to analyze ϵ_{II} numerically, because both ϵ_G and ϵ_F are usually unknown. For molten silver azide, however, a reasonable value for ϵ_G is at one's disposal. Obviously, the activation energy ϵ_I for decomposing the azide ion at a compact metal surface--a process which results in the formation of metallic silver--must be identical with ϵ_G, the activation energy for the one-dimensional growth of a compact silver nucleus. Substitute ϵ_I for ϵ_G in equation (3). Thus, one arrives at approximately 24 kcal for ϵ_F, the activation energy for the formation of new metal nuclei.

The physical significance of ϵ_F is as follows: Because ionic transport phenomena in heteropolar silver salts usually involve the transport of interstitial silver ions only, the basic process of nuclei formation in silver azide can be assumed to be the migration of excess silver ions to potential sites of nucleation, such as vacancies or impurities. Thus, the probability of forming new metal nuclei will be determined essentially by the number of potential sites, the number of excess (interstitial) silver ions, and the mobility of these ions in the azide matrix. The migration of interstitial ions in a lattice is governed by an activation energy of

$$\Phi = \frac{W_1}{2} + W_2 \qquad (4)$$

where W_1 denotes the energy for promoting an ion from its regular site to an interstitial position, and W_2 is the activation energy for cations to move from one interstitial position to another. Assume that the energy required for the silver ions to associate with the potential sites of nucleation is negligible. Then, the temperature dependence of the nucleation process will be given by $C \cdot \exp[\Phi]$, and Φ should be identical with $\epsilon_F = 24$ kcal/mole in equation (3). If the argument is valid, one can expect that other transport phenomena in silver azide which depend on interstitial silver ions should have the same temperature dependence as the formation of metal nuclei. In fact, Young (ref 6) measured an activation energy of 1.08 eV, or approximately 24.8 kcal/mole, for the temperature dependence of the ionic conductivity of silver azide. This value is in good agreement with the corresponding value of $\epsilon_F = 24$ kcal/mole from the decomposition experiments made in this study.

The physical meaning of an activation energy of 38 kcal/mole for the metal-azide interface reaction in the molten phase is not clear as yet. Bartlett, Tompkins, and Young related the activation energy for the solid

state decomposition to the energy necessary for thermal formation and subsequent dissociation of excitons N_3^*. In the absence of optical data on molten silver azide, such as the absorption spectrum and the ratio of the static to the high-frequency dielectric constant, and because of the lack of structural information on the melt, it is hardly possible to assess the validity for the molten silver azide of a similar exciton concept at the present time. On the other hand, it is interesting to note that the activation energies for the thermal dissociation of strictly covalent azides are very close to those measured for molten inorganic azides, such as AgN_3 and KN_3 (as shown in the table). The thermal decomposition of covalent azides is known to follow the pattern

$$RN_3 \rightarrow RN + N_2 \tag{5}$$

RN_3 is considered to resonate equally among the structures $R-\overset{..}{N}=N=\overset{+}{N}:^-$ and $R-\overset{-..}{N}-\overset{+}{N}\equiv N:$ (ref 7), and the activation energy for thermolysis is essentially the dissociation energy of the bond between the first and second nitrogen of the azido group.

Activation Energies for Thermal Decomposition of Azides

Compound	ϵ (kcal/mole)	Reference
methyl azide	40.8	*
	43.15	8
ethyl azide	40.1	9
	39.7	8
n-propyl azide	39.4	9
iso-propyl azide	38.5	9
silver azide (molten)	38	this paper
potassium azide (molten)	39	**

* M. S. O'Dell, private communication.
** H. J. Mueller, unpublished work.

The occurrence of an activation energy of 38–39 kcal/mole for molten azides raises the question to what extent a mode of decomposition given by equation (5) is possible in inorganic azide melts. Even though silver azide shows some covalency in its bond character, it has a prevalently ionic structure, and thus, a massive volume reaction, according to equation (5), cannot be expected. Experimental evidence, however, reveals that this reaction or one closely related is possible for inorganic azides at a metal interface. Clusius and Schumacher (ref 10) studied the electrolytical decomposition of an aqueous solution of isotopically center-labelled potassium azide, $K^{14}N^{15}N^{14}N$, as well as the thermolysis of this salt, and found that the species $^{15}N_2$ was practically absent in the decomposition products. They concluded that dissociation of the azide occurred by bond fracture $^{14}N - {}^{15}N^{14}N$. This, however, is essentially the decomposition pattern of organic azides, and an activation energy of the same magnitude can be expected for both organic and inorganic azides which decompose in the liquid phase at a metal surface. The experiments reported herein show that this is actually true.

Little can be said as to the intermediate steps of the melt decomposition. The presence of a metal interface in the reaction is essential for discharging the azide ions. Subsequent unimolecular decomposition of the azide radicals is unlikely because the easiest permitted reaction requires 62.3 kcal/mole (ref 11) as compared to the experimentally observed 38 kcal/mole. A ground state dissociation with only 7.5 kcal/mole is spin-forbidden, but could be of importance for decomposition in pairs via an N_6-intermediate. There is no evidence for the existence of such a species, however. The results obtained by Clusius and Schumacher, as well as the fact that the activation energies for organic and molten inorganic azides are practically identical, suggest that in both types of azides the decomposition must occur under similar configurational and energetical conditions, that is, the azido group must be attached to some sort of a radical by a covalent bond. With a metal interface, such a covalent bond could be established by chemisorption, and the following reaction steps at a metal speck $[Ag_x]$ are feasible:

$$[Ag_x] + N_3^- \rightarrow [Ag_x N - N_2]^-. \tag{6}$$

This first step amounts to the polarization and chemisorption of the azido group at the metal surface, while an essentially covalent surface bond is formed. When the necessary activation energy is available, bond fission occurs and gaseous nitrogen evolves:

$$[Ag_xN - N_2]^- + 38 \text{ kcal/mole} \rightarrow [Ag_xN]^- + N_2. \tag{7}$$

The remaining nitrogen radical may migrate on the surface and combine with another radical, followed by desorption of N_2. The excess charge of the metal speck becomes finally compensated by a silver ion:

$$[Ag_x]^- + Ag^+ \rightarrow [Ag_{x+1}]. \tag{8}$$

This reaction scheme would explain well the experimentally observed values of the activation energies, the $N-N_2$ bond fracture being the rate-determining step for the thermolysis of both organic and molten inorganic azides. Further investigations, however, will have to prove the foregoing hypothesis.

REFERENCES

1. Audubert, R. J., Chem. Phys., 49, 275 (1952).

2. Bartlett, B. E., Tompkins, F. C., and Young, D. A., Proc. Roy. Soc., 246, 206 (1958).

3. Yoffee, A. D., Proc. Roy. Soc., A208, 188 (1951).

4. Pfeiffer, H. G. Thesis at California Institute of Technology, 1948.

5. Jacobs, P. W. M. and Tompkins, F. C., Chemistry of the Solid State, edited by W. E. Garner. London: Butterworths Scientific Publications, 1955.

6. Young, D. A., Brit. J. Appl. Phys., 15, 499 (1964).

7. Pauling, L., The Nature of the Chemical Bond. Ithaca, New York: Cornell University Press, 1960.

8. Leermakers, J. A., J. Am. Chem. Soc., 55, 2719 (1933).

9. Geissler, G. and König, W., Z. Phys. Chem., 227, 81 (1964).

10. Clusius, K. and Schumacher, H., Helv. Chim. Acta, 41, 2264 (1958).

11. Gray, P., Quarterly Review, 17, 441 (1963).

DISTRIBUTION FOR USAERDL REPORT 1893

ADDRESSEE	NUMBER

Department of Defense

Assistant Secretary of Defense   1
ATTN: Technical Library
Washington, D. C. 20310

Director   1
Defense Atomic Support Agency
Washington, D. C. 20301

Defense Documentation Center   20
Cameron Station
Alexandria, Virginia 22314

Department of the Army

Chief of Research and Development   1
Department of the Army
Washington, D. C. 20310

Commanding General   1
U. S. Army Materiel Command
Director of Research and Development
ATTN: AMCRD-RC
Washington, D. C. 20315

Commanding Officer   1
U. S. Army Munitions Command
Frankford Arsenal
ATTN: Library
Philadelphia, Pennsylvania 19137

Commanding General   1
U. S. Army Mobility Equipment Command
4300 Goodfellow Blvd
St. Louis, Missouri 63120

DOCUMENT CONTROL DATA · R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1 ORIGINATING ACTIVITY (Corporate author)	2a REPORT SECURITY CLASSIFICATION
U. S. Army Engineer Research and Development Laboratories, Fort Belvoir, Virginia	Unclassified
	2b GROUP

3 REPORT TITLE

THE KINETICS OF THE THERMAL DECOMPOSITION OF MOLTEN SILVER AZIDE

4 DESCRIPTIVE NOTES *(Type of report and inclusive dates)*

Research Report

5 AUTHOR(S) *(Last name, first name, initial)*

Mueller, Dr. Herbert J.

6 REPORT DATE	7a TOTAL NO OF PAGES	7b NO OF REFS
March 1967	18	11

8a CONTRACT OR GRANT NO	9a ORIGINATOR'S REPORT NUMBER(S)
b. PROJECT NO	
c Task 1C014501A32B	1893
	9b OTHER REPORT NO(S) (Any other numbers that may be assigned this report)
d	

10 AVAILABILITY/LIMITATION NOTICES

Distribution of this document is unlimited.

11 SUPPLEMENTARY NOTES	12 SPONSORING MILITARY ACTIVITY
	U. S. Army Engineer Research and Development Laboratories Fort Belvoir, Virginia

13 ABSTRACT

    This report covers an investigation of the thermolysis of molten silver azide (AgN_3), which process is considered to be fundamental for the ignition of the explosive by thermal stimulus.

    The isothermal decomposition of molten silver azide was investigated in the temperature interval 309-340° C. Decomposition was found to occur at the metal-azide interface with an activation energy of 38 ± 2.5 kcal/mole. Initially, the decomposition proceeds at a constant rate. After a while, the reaction becomes accelerated as a result of the formation of silver nuclei in the melt. The rate of reaction is then proportional to the third power of time, and an apparent energy of activation of 138 ± 5 kcal/mole is measured. The activation energy for the growth of silver nuclei in the melt is estimated to be ca. 24 kcal/mole. The latter value can be interpreted as the activation energy for the migration of interstitial silver in the azide matrix.

DD ₁ FORM ₁ JAN 64 **1473**

14	KEY WORDS	LINK A		LINK B		LINK C	
		ROLE	WT	ROLE	WT	ROLE	WT
	Azides, explosives, kinetics.						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization (corporate author) issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers (either by the originator or by the sponsor), also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

(1) "Qualified requesters may obtain copies of this report from DDC."

(2) "Foreign announcement and dissemination of this report by DDC is not authorized."

(3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through

_____ ."

(4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through

_____ ."

(5) "All distribution of this report is controlled. Qualified DDC users shall request through

_____ ."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring (paying for) the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as (TS), (S), (C), or (U).

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

18